

## TECHNICAL DATA SHEET

# LARIPUR E 2103-90AE

**GENERAL DESCRIPTION** LARIPUR E 2103-90AE is a PTMG polyether-based TPU exhibiting very good hydrolytic stability and good microbial resistance. It is designed for injection moulding e.g. of tags and technical items, as well as for extrusion of hoses, cables, profiles and films.

**TYPICAL CHEMICAL-  
PHYSICAL PROPERTIES**

Parameter	Typical Value	Unit	Method
Density	1.14	gr/cm <sup>3</sup>	ISO 2781
Shore Hardness	90	A	ISO 7619-1
Abrasion Loss	30	mm <sup>3</sup>	ISO 4649
Tensile Modulus:	50%	7.7	N/mm <sup>2</sup>
	100%	9.3	
	300%	26.3	
Tensile Strength	61	N/mm <sup>2</sup>	ISO 22654
Elongation at Break	490	%	ISO 22654
Tear Strength	80	N/mm	ISO 34-1
Vicat Softening Point	105	°C	ISO 306
Compression set:	70h/23°C	22	%
	22h/70°C	44	

The above reported data do not constitute sales specifications for the material in object.

The properties reported in this Technical Data Sheet are determined on annealed, injection moulded specimens and represent the average of values obtained from a significant number of production lots.

The international standards above indicated are intended as a reference for the execution of the relative tests, whereas the choice of available options and any possible variation are detailed in our respective internal standards.

The informations reported in this Technical Data Sheet are based on our current best knowledge, however, even if we guarantee the quality consistency of our LARIPUR products, we reserve the option to periodically issue updated versions of this Technical Data Sheet and respective sale specifications as well.

The extrusion grade LARIPUR are identified by a specific end code (EG, EA, AE, DP, EM, EF, EP, U, EUV or HFM). This code has to be indicated when ordering those grades.



## STORAGE AND STABILITY

LARIPUR E 2103-90AE is supplied in regular pelletized form and packaged in 25 kg bags or 500 kg and 1000 kg octabins.

LARIPUR E 2103-90AE must be stored in its original and sealed containers and kept in a dry and well-ventilated place, avoiding the direct sun radiation.

The shelf life of LARIPUR E 2103-90AE is of six months from the date of delivery to the final customer, if stored in its original sealed packaging and in proper conditions.

## SAFETY

The product is not considered dangerous, nevertheless we recommend to read the Material Safety Data Sheet before handling.

## PROCESSING RECOMMENDATIONS

Before processing, material needs to be dried at 80-90°C for 3 hours, preferably using a dehumidifying drier fed by air with a dew point lower than -30°C.

Suggested moulding temperature profile:

Zone	Temperature
Zone 1	185°C
Zone 2	190°C
Zone 3	195°C
Nozzle	190°C

Suggested extrusion temperature profile:

Zone	Temperature
Zone 1	185°C
Zone 2	190°C
Zone 3	195°C
Zone 4	200°C
Adapter	195°C
Die	190°C

Being affected by the type of machine used, processing conditions and downstream equipment, the suggested temperature profiles has to be considered as just indicative.

Edition: 02 - 03/2019

## C.O.I.M.

Web site: [www.coimtpu.com](http://www.coimtpu.com)

Ever-Flaming Advanced  
Material Co., Ltd.  
Baotong Building, Baoan  
District, Shenzhen, Guangdong Province, China  
Phone: +86 75529565648  
Fax: +86 75529565685-806

九焱新材料(深圳)有限公司  
地址: 深圳市宝安区宝民一路宝通大厦  
Phone: +86 75529565648  
Fax: +86 75529565685-806