



Advanced Thinking

coim

LARIPUR®

LPR 7025

LPR 7025EG

Thermoplastic Polyurethane

**TECHNICAL DATA SHEET**

**Description:** LARIPUR 7025/7025EG is a polyester based TPU. The standard version is designed e.g. for injection molding application of technical items and tool overmoulding, while the EG version is used for hose, profile, film extrusion and compounding with other thermoplastic, too.

Physical Properties	Typical Value	Unit	Test Method
Specific Gravity	1.18	gr/cm <sup>3</sup>	DIN 53479
Shore Hardness	70	A	DIN 53505
Abrasion Loss	30	mm <sup>3</sup>	DIN 53516
Tensile Modulus:	50%	2.8	N/mm <sup>2</sup>
	100%	3.9	N/mm <sup>2</sup>
	300%	10.1	N/mm <sup>2</sup>
Tensile Strength	42	N/mm <sup>2</sup>	DIN 53504
Elongation at Break	680	%	DIN 53504
Tear Strength	70	N/mm	DIN 53515
VICAT Softening Point	60	°C	ISO 306
Compression Set:	70h/23°C	23	%
	22h/70°C	58	%

- The grade also suitable for extrusion are indicated by the EG or AE end code and consequently they have to be ordered with such code when used in this application.
- This technical note has been written on baseing our present best knowledge but the above mentioned data have not to be released as a specification for the material in object.
- Properties reported in this Data Sheet are determined on annealed specimens obtained by injected test plaques and mostly represent an average of values gathered from a significative number of production lots.
- Even if we guarantee the quality consistency of the LARIPUR products we could periodically issue up-dated version of this Technical Data Sheet and modify the respective sales specification as well.

Ever-Flaming Advanced  
Material Co., Ltd.  
Baotong Building, Baoan  
District, Shenzhen,  
Guangdong Province,  
China  
Phone: +86 755 29565648  
Fax: +86 755 29565685-806  
www.coimtpu.com

九焱新材料(深圳)有限公司  
地址: 深圳市宝安区宝民一路宝通大厦  
电话: 0755-29565648  
传真: 0755-29565685 转 806  
网址: www.coimtpu.com



Advanced Thinking

**coim**

**LARIPUR®**

**LPR 7025**

**LPR 7025EG**

**Thermoplastic Polyurethane**

**PROCESS RECOMMENDATION**

**Predrying Condition:** Material needs to be dried prior processing at 80°-90°C for 3 hours, preferably using a dehumidifying drier feeded by air exhibiting a dew point lower than -30°C.

**Processing**

**Recommended Molding Temperature Profile**

	°C
Zone 1	180
Zone 2	185
Zone 3	190
Nozzle	185

**Recommended Extrusion Temperature Profile**

	°C
Zone 1	175
Zone 2	180
Zone 3	190
Zone 4	185
Adapter	180
Die	175

*Being affected by type of machine used, processing condition and downstream equipment, the temperature profiles as given above has to be considered just as indicative.*

**Appearance** Trasparent. ( Evaluated on 6 mm thick test plaques )

**Approvals** **EC** and **FDA** food contact approved.

**Health and security** The product is not considered to be dangerous, nevertheless Safety Material Data Sheet is available upon request

**Supply and package** **LPR 7025/7025EG** is supplied in regular pellet form and it is packaged in 25 kg bags or 500 kg and 1000 kg octabins.

The information presented herein are given in good faith but without warranty. They are based on our experience, indicate our laboratory work results and do not necessarily indicate final product performance. We cannot be held liable for the results obtained with our products and for any loss or accident that may result from its use . Our suggestions do not release you from the obligation to check its validity and to test our products for both their process and end use application.COIM assumes no obligation or liability for the description, data and information given or result obtained as production testing and end product performance are the responsibility of the user. All our products are sold in accordance with our General Conditions of Sale. We don't make any warranties, express or implied, including, but not limited to the merchantability and fitness for a particular purpose.